
TexOpaque[™] 6000





↑ 6000-06D



Roller



Dye lot colours may vary.

D: White backing




Technical Specifications

PARAMETERS	TEXOPAQUE [™] 6000 SERIES	
standard width	182.9 cm (72")	
standard roll length	27.4 m (30 L/yd)	
weight (max.)	461 g/m² (13.6 oz/yd²)	
fabric thickness (max.)	0.33 mm (0.013")	
breaking strength		
warp (max.)	180 lbs/in.	
weft (max.)	150 lbs/in.	
composition	4-Ply laminated fiberglass (3 Ply PVC, 1 Ply fiberglass)	

Fire Classification (colours 6000-02 and 6000-07D): NFPA 701 (small scale), California U.S. Title 19, meets or exceeds most other CCC-C-521E type 2

Fire Classification (other colours): Boston Fire Dept. BFD 1x-1, California Fire Marshal Section 13115, NFPA 701 (small scale), U.S. Federal Government Spec. CCC-C-521E, CAN/ULC-S109-03 - Small and Large Flame Test

Bacteria & Fungal Resistance (colours 6000-02 and 6000-07D): ASTM G-21



TexOpaque™ is a trademark of Altex®.

Solar Heat Control Properties Interior Use - Zero Degree Profile Angle

(In accordance with ASHRAE Standard 74-1988)

	Solar optical properties				shading coefficient	shading coefficient
	100%			%	shade with:	shade with:
					single	insulating
FABRIC	TS	RS	AS	TV	1/4" HA	1" CL
6000-01	0	68	32	0	0.29	0.28
6000-02	0	68	32	0	0.29	0.28
6000-03	0	68	32	0	0.29	0.28
6000-04	0	68	32	0	0.29	0.28
6000-05	0	68	32	0	0.29	0.28
6000-06D	0	68	32	0	0.29	0.28
6000-07D	0	68	32	0	0.29	0.28
6000-08D	0	68	32	0	0.29	0.28
TS = Solar Transmission	I	V = Visible I	_ight Transm	nission	1/4" HA = 1/4" Heat Absorb	ing Glass 1" CL = 1" Clear Gla

RS = Solar Reflectance

AS = Solar Absorptance

The shading coefficient represents the percentage of solar heat gain coming into a room through the blind and glazing. It is marked between 0 and 1. A low percentage indicates a good protection against heat gain. Darker colours provide maximum glare reduction and visibility because they diffuse less light. For complete technical information, test results, performance specifications and larger samples, contact our Technical Department. Performance evaluations conducted by Matrix Inc. Cleaning instructions: Vacuum occasionally to prevent dust accumulation. Material can be washed on both sides using hot water and a mild detergent solution. If commercial spot cleaners are used, they must be tested and allowed to dry on an inconspicuous area to ensure compatibility.

Toronto 888.836.6980 | Vancouver 888.980.9899 | Montreal 800.363.5930 www.sunproject.com









*Varies by colour

1" CL = 1" Clear Glass